
	TECHNICAL SPECIFICATION	Nº: I-ET-0000.00-0000-431-P9U-002
	CLIENT: PETROBRAS	SHEET: 1 of 15
	JOB: RIGID OFFSHORE PIPELINES	CC
	AREA:	PROJECT:
DP&T	TITLE: WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	 EISE / EDR

INDEX OF REVISION

REV.	DESCRIPTION AND/OR REVISED SHEETS
0	ORIGINAL

	REV. 0	REV. A	REV. B	REV. C	REV. D	REV. E	REV. F	REV. G	REV. H
DATE	13/04/2018								
PROJECT	EISE/EDR								
EXECUTION	SG5H								
CHECK	UPL2								
APPROVAL	CLZ2								

THE INFORMATION CONTAINED IN THIS DOCUMENT IS PETROBRAS PROPERTY AND MAY NOT BE USED FOR PURPOSES OTHER THAN THOSE SPECIFICALLY INDICATED HEREIN. THIS FORM IS PART OF PETROBRAS N-381 REV. L



TECHNICAL SPECIFICATION

Nº I-ET-0000.00-0000-431-P9U-002

REV. 0

JOB: RIGID OFFSHORE PIPELINES

SHEET: 2 of 15



TITLE: WET THERMAL INSULATION FOR SUBSEA EQUIPMENT

NP-1

EISE / EDR

INDEX

1. SCOPE OF DOCUMENT.....	3
2. WET THERMAL INSULATION REQUIREMENTS.....	3
3. ADDITIONAL, MODIFIED AND DELETED REQUIREMENTS FOR WET THERMAL INSULATION APPLICATION RELATED TO ISO 12736.....	3

	TECHNICAL SPECIFICATION	Nº I-ET-0000.00-0000-431-P9U-002	REV. 0
	JOB:	RIGID OFFSHORE PIPELINES	
	TITLE:	WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	
		SHEET:	3 of 15
		 EISE / EDR	

1. SCOPE OF DOCUMENT

- 1.1 This Technical Specification defines the minimum requirements related to the application of wet thermal insulation on subsea equipment.
- 1.2 CONTRACTOR shall fulfill all the requirements presented within this Technical Specification.
- 1.3 This document shall be read in conjunction with the following standards and Technical Specifications:
- ISO 12736 – First Edition
Title: Petroleum and natural gas industries – Wet thermal insulation coatings for pipelines, flow lines, equipment and subsea structures;
 - I-ET-0000.00-0000-210-P9U-001
Title: Pipeline Field Joint Coating and Field Repair of Linepipe Coating;
- 1.4 In case it is noted any sort of conflict between this Technical Specification and the aforementioned documents, the following precedence order shall be respected:
- a) This Technical Specification;
 - b) ISO 12736;
 - c) I-ET-0000.00-0000-210-P9U-001.

2. WET THERMAL INSULATION REQUIREMENTS

- 2.1 CONTRACTOR shall fulfill the requirements of the following document for the insulation coating manufacturing:
- ISO 12736 – First Edition
Title: Petroleum and natural gas industries – Wet thermal insulation coatings for pipelines, flow lines, equipment and subsea structures;
- 2.2 There are some additional and modified requirements which shall be fulfilled by CONTRACTOR. Additional and modified requirements to the aforementioned document are highlighted in this Technical Specification considering the following expressions:
- [ADDITION] – When CONTRACTOR shall consider additional requirements.
 - [MODIFICATION] – When a partial or full modification in the referred item is required.
 - [DELETED] – When the referred item shall be entirely disregarded by CONTRACTOR.
- 2.3 In case of custom insulation coatings are envisaged by CONTRACTOR and this type of insulation is not included within this document it can be pre-qualified following the same structure and requirements of this document before been proposed to PETROBRAS.
- 2.4 CONTRACTOR may propose custom insulation coatings not included within this Technical Specification since the insulation coating system is submitted to a pre-qualification program. The pre-qualification program shall be executed before its proposal to PETROBRAS and shall have the same structure and requirements described herein.

3. ADDITIONAL, MODIFIED AND DELETED REQUIREMENTS FOR WET THERMAL INSULATION APPLICATION RELATED TO ISO 12736.



- 3.1 The items mentioned below follow the sequence already defined within the ISO 12736. The standard section number is given in brackets.

Introduction

() Modification: “It is necessary that users of this ISO 12736 be aware that further or differing requirements can be required for individual applications.”

Scope

(1) Modification: “This International Standard defines the minimum requirements for qualification, application, testing, handling, storage and transportation of new and existing wet thermal insulations systems for

	TECHNICAL SPECIFICATION	Nº I-ET-0000.00-0000-431-P9U-002	REV. 0
	JOB:	RIGID OFFSHORE PIPELINES	
	TITLE:	WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	
		SHEET:	4 of 15
		 EISE / EDR	

equipment and subsea structures in the petroleum and natural gas industries. The purpose of the system is to provide thermal insulation.”

Normative references

(2) Addition: “I-ET-0000.00-0000-210-P9U-001, Pipeline Field Joint Coating and Field Repair of Linepipe Coating.”

Terms and definitions

(3.22) Modification: “Pi tape: precision vernier periphery tape that allows the direct measurement of the diameter of tubular objects without the need for calipers or micrometers.”

Acronyms

- (4) Deleted: “4LPP four layer polypropylene.”
- (4) Addition: “5LPP five layer polypropylene.”
- (4) Addition: “HGM hollow glass microspheres.”

Qualification Dossier

(6.1) Modification: “A qualification dossier of the proposed insulation system in accordance with this clause shall be presented by the system supplier for review. The requirements of this clause shall apply to all layers present in the insulations system. The content of such a dossier shall be in accordance with 6.2 and 6.3.”

(6.1) Addition: “Historical data shall have been approved by a Third Party Inspection Company or PETROBRAS representative.”

(6.3) Deleted: “The wet insulation system supplier can select any anti-corrosion coating believed to be suitable for the maximum rated temperature of its insulation system and with which the system will pass the qualification requirements of this International Standard.”

(6.3) Addition: “The anticorrosion coating system shall be indicated by PETROBRAS through a Coating Assessment Technical Specification.”

Layer test requirements

(7.1) Modification: “Table 2 specifies properties to be tested. Tests are mandatory.”

(Table 1) Modification: “Test procedure for Hydrostatic compressive behavior shall be ‘Tri-axial compression and creep test’.”



(Table 1) Addition: “The test period of ‘tri-axial compression and creep test’ shall be at least 28 days and test period shall be enough in order to allow the extrapolation of data for 30 years.”

(Table 1) Addition: “Water absorption: it shall be considered a test period necessary for the sample to saturate in water at 23°C ± 1°C. Method 1 of ISO 62 shall be adopted. The test period shall be enough in order to allow the extrapolation of data for 30 years.”

(7.2) Addition: “These tests are mandatory and their performance shall be witnessed by a Third Party Inspection Company or an end user representative.”

(7.2.4) Deleted.

(7.2.5) Addition: “In order to demonstrate the suitability of the material to UV exposure, the insulation material shall be tested in accordance with ISO 21809-1 Annex G. It shall be considered a test period of 3000 hours. In case insulation is not based on PE or PP material CONTRACTOR shall propose UV resistance tests.”

	TECHNICAL SPECIFICATION	Nº I-ET-0000.00-0000-431-P9U-002	REV. 0
	JOB:	RIGID OFFSHORE PIPELINES	
	TITLE:	WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	
		SHEET:	5 of 15
		 EISE / EDR	

Insulation system test requirements

(8.1) Modification: In case tests parameters defined by insulation system supplier is out of range of specific project design conditions the tests shall be performed again within the correct range.”

(8.1) Deleted: “If applicable, testing shall include a field joint applied in accordance with the requirements of Clause 10.”

(Table 3) Deleted: “Field joints (8.2.8).”

(8.2.2) Modification: “Baseline tests (mandatory).”

(8.2.2) Modification: “The following tests shall be carried out on the complete insulation system prior to any simulated installation or...”

(8.2.2) Modification: “- CD test shall be performed at 23°C for 28 days in accordance with project Coating Assessment Technical Specification.”

(8.2.3) Deleted.

(8.2.4) Deleted.

(8.2.5) Deleted.

(8.2.7) Deleted.

(8.2.8) Deleted.

(8.2.9) Modification: “Simulated service test (subsea equipment) (mandatory).”

(8.2.9) Modification: “- confirm that the cool down time and define the U-value of the insulation system when subjected to...”

(8.2.9) Modification: “adhesion test or peel test (8.2.2) shall be carried out for comparison with baseline tests.”

(8.2.9) Modification: “samples of the insulation material shall be taken from the test piece after completion of the simulated service testing and subjected to the material property testing described in 7.1. To be performed only the following tests: density, tensile properties, and hardness. Acceptance criteria in the range as obtained in 7.1.”

Application process and quality control

(9.1) Modification: “If other system types are used, this clause shall be used as.....”



(9.3) Addition: “In order to speed up the approval process of APS and ITP, documents may be issued as independent documents.”

(9.4) Modification: “The APS shall be qualified by a PQT. Test methods, acceptance criteria and frequencies for PQT shall be specified in the ITP.”

(9.4) Addition: “If the proposed coating system has been already qualified by PETROBRAS, the specific conditions demanding the execution of a new PQT are as follows:

Key Variable	Specific conditions requiring a new full PQT
Insulation material	Change of any coating material composing the insulation system
Equipment	Change of methodology for the coating application
Volume of material produced	Range of volume of material produced are to be qualified during PQT
Insulation thickness OD	Range of variation in thickness of coating are to be defined during PQT
Key process parameters	Out of the tolerance previously qualified (e.g. temperatures, pressure of extrusion/pumping, rotation of the screw/pump flow, etc.)
Qualification dossier	As per item 6

(9.4) Addition: “In case of projects with Clad/Lined pipes, the PQT may be carried out using carbon steel pipes. Nevertheless a further demonstration shall be done in a later stage considering all the necessary actions to be taken along the coating process in order to avoid the contamination of CRA material.”

	TECHNICAL SPECIFICATION	Nº I-ET-0000.00-0000-431-P9U-002	REV. 0
	JOB:	RIGID OFFSHORE PIPELINES	
	TITLE:	WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	
			SHEET: 6 of 15
			 EISE / EDR

(9.4) Modification: “The PQT shall be carried out in presence of the PETROBRAS and designated CONTRACTOR’s representative, if applicable.”

(9.5) Modification: “A PPT is not required in case the PQT is developed in the same yard of the final insulation application.”

(9.6.2) Deleted.

Polyurethane applied in liquid form

(9.6.3.1) Modification: “Polyurethane is applied in liquid form using suitable dispensing equipment. It may be either in solid or syntactic form.”



(9.6.3.1) Modification: “The suitable anticorrosion coating shall be in accordance with the project specific Coating Assessment Technical Specification.”

(Table 6) Modification: “Table 6 – Minimum inspection and testing requirements for PU.

Property	Units	Test method	Requirements	Frequency		
				PQT	PPT	Production
Raw material testing (Manufacturer’s data)						
Density (polyol)	Relative to water at 1.0	Manufacturer’s method	Within the manufacturer’s certificate of conformity range	Each batch	Each batch	Each batch
Viscosity (polyol)	cPs	ISO 3104 or ISO 3219	Within the manufacturer’s certificate of conformity range	Each batch	Each batch	Each batch
Gel time of mixed system (polyol + iso)	s	Manufacturer’s method	Within the manufacturer’s certificate of conformity range	Each batch	Each batch	Each batch
Hardness of cured system	Shore A or Shore D	ISO 868	Within the manufacturer’s certificate of conformity range	Each batch	Each batch	Each batch
Isocyanate content	%	ISO 14896	Within the manufacturer’s certificate of conformity range	Each batch	Each batch	Each batch
Density (glass microspheres)	g/cm ³	Manufacturer’s method	0.35 ≤ ρ ≤ 0.41	Each batch	Each batch	Each batch
Crush strength (glass microspheres)	%	Manufacturer’s method	≥ 80% minimum fraction survival at 5500 psi ≥ 90% target fraction survival at 5500 psi	Each batch	Each batch	Each batch
Substrate preparation						
Environmental conditions and substrate temperature	°C	ISO 8502-4	Minimum 3°C above dew point	Each item	Each item	Start of each shift
Anticorrosion coating surface preparation	-	Visual	If applicable, abrasion with sand paper grit 50 minimum and dust vacuum cleaning	Each item	Each item	Each item
Adhesion promoter application (if required)						
Material Certificate	-	-	Conformity certificate issued by manufacturer.	Each batch	Each batch	Each batch
Pot life	min	Stop watch	Cure time check in accordance with manufacturer’s recommendation	Each batch	Each batch	Each batch
Mix ratio	Ratio by	Weight	Ratio and tolerance according to manufacturer’s	Start of	Start of	Each shift

		TECHNICAL SPECIFICATION		Nº I-ET-0000.00-0000-431-P9U-002		REV. 0	
		JOB: RIGID OFFSHORE PIPELINES				SHEET: 7 of 15	
		TITLE: WET THERMAL INSULATION FOR SUBSEA EQUIPMENT				 EISE / EDR	
	weight	measurement	recommendation	PQT	PPT		
Visual appearance	-	Visual	Within manufacturer's recommendation. Comparative visual test panels from PQT.	Each item	Each item	Each item	
PU application							
Mix ratio	Ratio by weight	Weight measurement	As per manufacturer's recommendation with a maximum variation of $\pm 2\%$	Start of PQT	Start of PPT	Once per shift or at start of each pouring	
Verification of raw material properties by a "cup shot"	Visual	Cured 500cm ³ (approximately) fixed mass sample at 23°C	Good mixing. No air, no discoloration from unmixed components, etc.	Start of PQT	Start of PPT	Start of each shift	
Gel time check (machine dispensed)	s	Stop watch	To be used as reference for maximum pour time limitations	Once	Once	Once per shift	
Visual inspection of the mould prior to moulding	-	Visual	Clean, no adhering PU. Releasing agent applied on entire inner surface of the mould.	Each item	Each item	Each pipe	
Raw material processing temperature	°C	Thermocouple	As per manufacturer's recommendation	Once	Once	Once per shift	
Mould temperature	°C	Thermocouple	Acceptable range to be established during PQT	Each item	Each item	Monitor continuously and record once per hour	
Anticorrosion coating surface temperature	°C	Contact thermometer	Acceptable range to be established during PQT	Each item	Each item	Monitor continuously and record once per hour	
Minimum demoulding time	s	Stop watch	Acceptable range to be established during PQT	Each item	Each item	Monitor continuously and record once per hour	
Hardness immediately after demoulding	Shore A	ISO 868 or ASTM D2240	≥ 50	Each item	Each item	Each item	
Laboratory testing							
Density	kg/m ³	ISO 1183 or ASTM D792	In accordance with thermal insulation design (test at 23°C $\pm 2^\circ\text{C}$)	Once for PQT	Once for PPT	Once per shift	
Tensile strength at yield	MPa	ISO 527 or ASTM D638	In accordance with thermal insulation design (test at 23°C $\pm 2^\circ\text{C}$)	Once for PQT	Once for PPT	Once per shift	
Elongation at break	MPa	ISO 527 or ASTM D638	In accordance with thermal insulation design (test at 23°C $\pm 2^\circ\text{C}$)	Once for PQT	Once for PPT	Once per shift	
Modulus of elasticity	MPa	ASTM D638	In accordance with thermal insulation design (test at 23°C $\pm 2^\circ\text{C}$)	Once for PQT	Once for PPT	Once per shift	

	TECHNICAL SPECIFICATION		Nº I-ET-0000.00-0000-431-P9U-002	REV. 0		
	JOB: RIGID OFFSHORE PIPELINES				SHEET: 8 of 15	
	TITLE: WET THERMAL INSULATION FOR SUBSEA EQUIPMENT				 EISE / EDR	
Secant modulus	MPa	ASTM D638	In accordance with thermal insulation design (test at 23°C ± 2°C)	Once for PQT	Once for PPT	Once per shift
Compressive strength	MPa	ISO 844	In accordance with thermal insulation design (test at 23°C ± 2°C)	Once for PQT	Once for PPT	N/A
Thermal conductivity	W/(m.K)	ISO 8301	In accordance with thermal insulation design (test at 23°C ± 2°C)	5 tests on 2 pipes (total 10 samples)	3 tests	N/A
Hydrostatic strength – Tri-axial compression and creep test	%	Annex A	≤ 5% (extrapolated to 20 years). Test to be performed at a pressure ≥ 1.1*(Maximum water depth) during 28 days.	3 tests	N/A	N/A
Mass ratio of glass microspheres (GSPU)	%	Annex J	Acceptable range to be established during PQT	Each item	2 items	Once per shift
Glass microspheres density after processing (GSPU)	%	Annex J	Acceptable range to be established during PQT	Each item	2 items	Once per shift
Entrapped air ratio (GSPU)	%	Annex J	Acceptable range to be established during PQT	Each item	2 items	Once per shift
Adhesion pull off	MPa	ISO 4624	≥ 5MPa	Each item	Each item	Once per shift
Hardness	Shore A or Shore D	ISO 868 or ASTM D2240	Within manufacturer's certificate of conformity range	Each item	Each item	Each item
Insulation thickness	mm	PI tape or electronic equipment	In accordance with thermal insulation design	Each item	Each item	Each item
Concentricity (for pipes only)	mm	Straight edge ruler or electronic equipment at cutback area	± 10% of nominal thickness, but not greater than 4mm	Each item, 8 measurements	Each item, 8 measurements	Once per shift
Ovality (for pipes only)	%	Caliper and PI tape	$(OD_{max} - OD_{min})/OD_{PI\ tape} < 2$	Each item	Each item	1 st pipe then every 20 th pipe
Cutback	mm	Measurement	By agreement	Each item	Each item	Each item
Removal of release agent	-	Visual	-	Each item	Each item	Each item
Visual inspection	-	Visual	Mouldings are free from large air traps, porosity, debris, knit lines, cavities, cracks and disbondments at joints and substrate interfaces. Cosmetic surface faults may be accepted.	Each item	Each item	Each item
PU foam application using spray or injection method with extruded polyolefin outer jacket (9.6.3.2) Deleted.						



	TECHNICAL SPECIFICATION	Nº I-ET-0000.00-0000-431-P9U-002	REV. 0
	JOB:	RIGID OFFSHORE PIPELINES	
	TITLE:	WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	
			SHEET: 9 of 15
			 EISE / EDR

Silicone insulation systems



(9.6.3.4) Modification: "The application of pre-cast forms is not acceptable for linepipes and subsea equipment."

(Table 8) Modification: "Table 8 – Minimum inspection and testing requirements for silicone"

Property	Units	Test method	Requirements	Frequency		
				PQT	PPT	Production
Raw material testing (Manufacturer's data)						
Viscosity	cPs	ISO 2884	Within the manufacturer's certificate of conformity range	Each batch	Each batch	Each batch
Gel time	min	Manufacturer	Within the manufacturer's certificate of conformity range	Each batch	Each batch	Each batch
Hardness of cures system	Shore A	ISO 868 or ASTM D2240	Within the manufacturer's certificate of conformity range	Each batch	Each batch	Each batch
Density	kg/m ³	ISO 1183-1	Within the manufacturer's certificate of conformity range	Each batch	Each batch	Each batch
Tensile properties (modulus, elongation at break, tensile strength at break)	MPa %	ISO 37	Within the manufacturer's certificate of conformity range	Each batch	Each batch	Each batch
Density (glass microspheres) if applicable	g/cm ³	Manufacturer	0.35 ≤ ρ ≤ 0.41	Each batch	Each batch	Each batch
Crush strength (glass microspheres) if applicable	MPa	Manufacturer	≥ 80% minimum fraction survival at 5500 psi ≥ 90% target fraction survival at 5500 psi	Each batch	Each batch	Each batch
Substrate preparation						
Environmental conditions and substrate temperature	°C	ISO 8502-4	Minimum 3°C above dew point	Each item	Each item	Start of each shift
Anti-corrosion coating surface preparation	-	Visual	If applicable, abrasion with sand paper grit 50 minimum and dust vacuum cleaning	Each item	Each item	Each item
Adhesion promoter application						
Over coating time	s	-	Time check in accordance with manufacturer's recommendation	Each item	Each item	Each item
Visual appearance	-	Visual	Within manufacturer's recommendation. Comparative visual test panels from PQT	Each item	Each item	Each item
Silicon application						
Mix ratio	Ratio by weight	Weight measurements	± 5% from manufacturer's data sheet	One item	One item	Once per shift
Verification of raw material properties by a "cup shot"	Visual	Cured 500cm ³ (approximately) fixed mass sample at 23°C	Good mixing. No air, no discoloration from unmixed components, etc.	Start of PQT	Start of PPT	Start of each shift

		TECHNICAL SPECIFICATION		Nº I-ET-0000.00-0000-431-P9U-002		REV. 0		
		JOB: RIGID OFFSHORE PIPELINES					SHEET: 10 of 15	
		TITLE: WET THERMAL INSULATION FOR SUBSEA EQUIPMENT					 EISE / EDR	
Visual inspection of the mould	-	Visual	Clean, without any contamination	Each pipe	Each pipe	Each pipe		
Laboratory testing								
Density	kg/m ³	ISO 1183	In accordance with thermal insulation design (test at 23°C ± 2°C)	Once	Once	Once per shift		
Tensile strength and elongation at break	MPa %	ISO 37	Within the manufacturer's certificate of conformity range	One test	One test	N/A		
Compressive strength	MPa	ISO 844	Within the manufacturer's certificate of conformity range	Each pipe	N/A	N/A		
Adhesion (pull off)	MPa	ISO 4624	≥ 5MPa	Each pipe	Each pipe	Once per shift		
Thermal conductivity	W/m.K)	ISO 8301	In accordance with thermal insulation design (test at 23°C ± 2°C)	3 samples	3 samples	N/A		
Final inspection								
Hardness	Shore A	ISO 868	Within the manufacturer's certificate of conformity range	Each item	Each item	Each item		
Insulation thickness	mm	PI tape or electronic equipment or vent port	In accordance with thermal insulation design	Each item	Each item	Each item		
Concentricity (for pipes only)	mm	Straight edge ruler or electronic equipment at cutback area	± 10% of nominal thickness, but not greater than 4mm.	Each pipe, 8 measurements	Each pipe, 8 measurements	Once per shift		
Ovality (for pipes only)	%	Caliper and PI tape	$(OD_{max} - OD_{min})/OD_{PItape} < 2$	Each pipe	Each pipe	1 st pipe then every 20 th pipe		
Cutback	mm	Tape measurement	In accordance with thermal insulation design	Each item	Each item	Each item		
Visual inspection	-	Visual and optical microscope	Free of voids, blisters, cracks and separation from anticorrosion coating.	Each item	Each item	Each item		
<p>”</p> <p>Rubber coating on steel (9.6.5.2) Deleted.</p> <p>Rubber coating on other materials (Table 10) Modification: “Table 10 – Minimum inspection and testing requirements for rubber on to other materials</p>								
Property	Units	Test method	Requirements	Frequency				
				PQT	PPT	Production		
Raw material testing (Manufacturer's data)								
Vulcanization characteristics	Nm	ISO 6502	Within the manufacturer's certificate of conformity range. Vulcanization curve	Each batch	Each batch	Each batch		

	TECHNICAL SPECIFICATION		Nº I-ET-0000.00-0000-431-P9U-002	REV. 0		
	JOB: RIGID OFFSHORE PIPELINES			SHEET: 11 of 15		
	TITLE: WET THERMAL INSULATION FOR SUBSEA EQUIPMENT			 EISE / EDR		
			and parameters values to be supplied.			
Hardness	Shore A	ISO 7619-1	Within the manufacturer's certificate of conformity range	Each batch	Each batch	Each batch
Density	kg/m ³	ISO 2781	Within the manufacturer's certificate of conformity range	Each batch	Each batch	Each batch
Substrate preparation						
Environmental conditions and substrate temperature	°C	ISO 8502-4	Minimum 3°C above dew point	Each item	Each item	Start of each shift
Surface conditions prior to preparation	-	Visual Inspection	No oil, grease or similar contaminations	Each item	Each item	Each item
Substrate surface preparation	-	Visual	If applicable, abrasion with sand paper grit 50 minimum and dust vacuum cleaning	Each item	Each item	Each item
Rubber primer application						
Environmental conditions and substrate temperature	°C	ISO 8502-4	Minimum 3°C above dew point	Each item	Each item	Each item
Over coating time	min	-	Time check in accordance with manufacturer's recommendation	Each item	Each item	Each item
Visual appearance	-	Visual	Within manufacturer's recommendation. Comparative test panels from PQT	Each item	Each item	Each item
Rubber application						
Vulcanization temperature	°C	Contact thermometer couple	Acceptable range to be established during PQT	Each item monitored	Each item monitored	Each item monitored
Vulcanization time	min	Stop watch	Acceptable range to be established during PQT	Each item	Each item	Each item
Vulcanization pressure	MPa	Manufacturer specification	Acceptable range to be established during PQT	Each item	Each item	Each item
Laboratory testing						
Thermal conductivity	W/(m.K)	ISO 8301	In accordance with thermal insulation design (test to be performed at 23°C ± 2°C)	Once ^a	Once ^a	N/A
Specific heat capacity	J/(kg.K)	ISO 11357	In accordance with thermal insulation design (test to be performed at 23°C ± 2°C)	Once ^a	Once ^a	N/A
Tensile strength and elongation at break	MPa %	ISO 37	Within manufacturer's certificate of conformity range	Once ^b	Once ^b	N/A
Tear strength	N/mm	ISO 34	Within manufacturer's certificate of conformity range	Once ^b	Once ^b	N/A
Density	g/cm ³	ISO 2781	In accordance with thermal insulation design (test to be performed at 23°C ± 2°C)	Once	Once	N/A

	TECHNICAL SPECIFICATION	Nº I-ET-0000.00-0000-431-P9U-002	REV. 0
	JOB:	RIGID OFFSHORE PIPELINES	
	TITLE:	WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	
		SHEET: 12 of 15	
		 EISE / EDR	



Adhesion test / peel test (on pipe or test plate)	N/mm	ISO 21809-1 ISO 813	Acceptable range do be defined during PQT, but must be greater than 2.5N/mm	Once per pipe	Once per pipe	Each vulcanization batch
Final inspection						
Hardness	Shore A	ISO 7619-1	Within manufacturer's certificate of conformity range	Each item	Each item	Each item
Total insulation thickness	mm	PI tape or electronic equipment	In accordance with thermal insulation design	Each item	Each item	Each item
Concentricity (for pipes only)	mm	Straight edge ruler or electronic equipment at cutback area	± 10% of nominal thickness, but not greater than 4mm	Each pipe, 8 measurements	Each pipe, 8 measurements	Once per shift
Ovality (for pipes only)	%	Caliper and PI tape	$(OD_{max} - OD_{min})/OD_{PI\text{tape}} < 2$	Each pipe	Each pipe	1 st pipe then every 20 th pipe
Cutback	mm	Tape measurement	In accordance with thermal insulation design. No disbondment between layers or defects/voids	Each item	Each item	Each item
Visual inspection	-	Visual	Free from defects	Each item	Each item	Each item
a Middle layer only, due to the difficulty of machining proper samples from thin inner and outer layer.						
b Middle and outer layer only, due to the difficulty of machining proper samples from thin inner layer.						

Epoxy insulation systems

(Table 11) Modification: "Table 11 – Minimum inspection and testing requirements for epoxy systems

Property	Units	Test method	Requirements	Frequency		
				PQT	PPT	Production
Raw material testing (Manufacturer's data)						
Wet density	kg/m ³	ISO 2811-1	Within the manufacturer's certificate of conformity range	Each batch	N/A	Each batch
Gel time of system	h	0.5 mass at 23°C	Within the manufacturer's certificate of conformity range	Each batch	N/A	Each batch
Hardness of cured system	Shore A/D	ISO 868	Within the manufacturer's certificate of conformity range	Each batch	Each batch	Each batch
Density (glass micro-spheres)	kg/m ³	Manufacturer	$0.35 \leq \rho \leq 0.41$	Each batch	Each batch	Each batch
Crush strength (glass micro-spheres)	psi	????	≥ 80% minimum fraction survival at 5500 psi ≥ 90% target fraction survival at 5500 psi	Each batch	Each batch	Each batch
Hydrostatic Compression	MPa	Annex A	Within the manufacturer's certificate of conformity range	Once for PQT	N/A	N/A
Substrate preparation						
Environmental conditions and	°C	ISO 8502-4	Minimum 3°C above dew point	Each item	Each item	Start of each shift

	TECHNICAL SPECIFICATION		Nº I-ET-0000.00-0000-431-P9U-002	REV. 0		
	JOB: RIGID OFFSHORE PIPELINES				SHEET: 13 of 15	
	TITLE: WET THERMAL INSULATION FOR SUBSEA EQUIPMENT				 EISE / EDR	
substrate temperature						
Surface conditions prior to preparation		Visual Inspection	No oil, grease or similar contaminations	Each item	Each item	Each item
Anticorrosion coating surface preparation	-	Visual	If applicable, abrasion with sand paper grit 50 minimum and dust vacuum cleaning	Each item	Each item	Each item
Epoxy application						
Mix ratio	ratio by weight	Weight measurement	As per manufacturer's recommendation with a maximum of $\pm 5\%$.	Once	Once	At each application
Verification of raw material properties by a "cup shot"	Visual	Cured 0.5l fixed mass sample at 23°C	Good mixing. No air, no discolouration from unmixed components, etc	Start of PQT	Start of PPT	Start of each application
Visual inspection of mould prior to filling	Visual	-	Clean, with no debris	Each item	Each item	Each item
Mould temperature	°C	Thermocouple	Acceptable range to be established during PQT	Each item	Each item	Each item
Exotherm temperature during moulding	°C	Thermocouple	Acceptable range to be established during PQT. The exotherm should be checked at the centre of the maximum thickness during cure	One item	One item	N/A
Laboratory testing						
Cured density	kg/m ³	ISO 1183 Method A	In accordance with thermal insulation design (test to be performed at 23°C \pm 2°C)	Once for PQT	Every batch of raw material	Once per shift
Glass transition temperature	°C	ISO 11357-2	In accordance with thermal insulation design	Once for PQT	Every batch of raw material	Once per shift
Mass ratio of glass microspheres	%	As per Annex I	Acceptable range to be established during PQT	Each item	2 items	Once per shift
Glass microspheres density after processing	%	As per Annex I	Acceptable range to be established during PQT	Each item	2 items	Once per shift
Entrapped air ratio	%	As per Annex I	Acceptable range to be established during PQT	Each item	2 items	Once per shift
Tensile strength and elongation at break	MPa	ISO 527	Within manufacturer's certificate of conformity range	One test	N/A	N/A
Adhesion	MPa	ISO 4624	Pull off test > 5 MPa or acceptable range to be established during PQT	Each item	Each item	Once per shift
Thermal conductivity	W/(m.K)	ISO 8301	In accordance with thermal insulation design (test to be performed at 23°C \pm 2°C)	Once for PQT	Every batch of raw material	N/A
Hydrostatic Compression	MPa	As per Annex A	In accordance with thermal insulation design (test to be	Once for PQT	Every batch of raw	N/A

	TECHNICAL SPECIFICATION	Nº I-ET-0000.00-0000-431-P9U-002	REV. 0
	JOB:	RIGID OFFSHORE PIPELINES	
	TITLE:	WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	
		SHEET: 14 of 15	
		 EISE / EDR	

			performed at 23°C ± 2°C)		material	
Final inspection						
Hardness	Shore D	ISO 868	Within manufacturer's certificate of conformity range	Each item	Each item	Each item
Insulation thickness	mm	PI tape or electronic equipment	In accordance with thermal insulation design	Each item	Each item	Each item
Concentricity (for pipes)	mm	Straight edge ruler or electronic equipment at cutback area	± 10% of nominal thickness, but not greater than 4mm	Each pipe, 8 measurements	Each pipe, 8 measurements	Once per shift
Ovality (for pipes)	%	Caliper and PI tape	$(OD_{max} - OD_{min})/OD_{PI\text{tape}} < 2$	Each item	Each item	1 st pipe then every 20 th pipe
Cutback	mm	Tape measurement	In accordance with thermal insulation design. No disbondment between layers or defects/voids	Each item	Each item	Each item
Visual inspection	-	Visual	Mouldings are free from air traps, porosity, debris, knit lines, cavities and disbondments at joints and substrate interfaces. Cosmetic surface faults may be accepted	Each item	Each item	Each item

”

Phenolic insulation systems

(9.6.7) Deleted.

Requirements for field joints

(10) Deleted.

Handling, storage and transportation requirements

(11) Addition: “A specific procedure encompassing the operations of handling, storage at coating yard and also the transportation shall be supplied to PETROBRAS’ for approval.”

(11) Addition: “The partial thermal insulation coating shall be protected from UV degradation ‘between passes’ (if applicable).”

(11) Addition: “Regarding the storage of insulated equipment, the equipment shall be covered all the time.



Hydrostatic compressive behavior/Tri-axial test procedures

(A.1) Modification: “Hydrostatic test is not acceptable for evaluation of thermal insulation coating systems mentioned within this Technical Specification. The tri-axial compression and creep test procedure shall be used.”

(A.3) Modification: “The duration of the test is 28 days.”

Simulated bend test

(Annex B) Deleted.

	TECHNICAL SPECIFICATION	Nº I-ET-0000.00-0000-431-P9U-002	REV. 0
	JOB:	RIGID OFFSHORE PIPELINES	
	TITLE:	WET THERMAL INSULATION FOR SUBSEA EQUIPMENT	
		SHEET: 15 of 15	
			
		EISE / EDR	

Cyclic (fatigue) bend test

(Annex C) Deleted.

Simulated tensioner test

(Annex D) Deleted.

Simulated service test (factory applied coating)

Deleted.

Simulated service test (field joint)

(Annex G) Deleted.

Simulated service test (subsea equipment)

Addition: "On completion of the test and/or at one or more agreed points during test, a cooldown simulation using an active cooldown cycle approach is required."

Ring shear test procedure

Deleted.